



# Product information | TECHNICAL DATA SHEET

**GESSO PRIMER.** Prepares and primes surfaces to be painted. 400 ml, 13 0z, 370 g.

### **GENERAL DESCRIPTION**

Product developed for preparing, sealing, priming and improving color adhesion to most surfaces

## FEATURES

- Fast drying.
- Excellent flexibility.
- Easy to apply and repaint.
- Excellent adherence.
- Does not contain lead.
- High opacity.

#### **APPLICATIONS**

Suitable for the preparation of canvas, wood, paper and metal. Do not use for the preparation of plastics or perform a test prior to use.

- DIY

- Arts & crafts. - Fine arts.

#### INSTRUCTIONS FOR USE

- Shake well before use, one minute after hearing the sound of mixer.
- Apply over dry and cleaned surfaces. Remove corrosion. Over PP apply first a primer.
- Apply in thin coats to achieve better results, three thin coats are better than one thick coat.
- After use, turn can upside down and depress valve button for several seconds until only gas emerges so as to prevent clogging.
- Invertir el aerosol para purgar la válvula tras el uso, si se atasca el difusor reemplazarlo por uno de nuevo.
- Don't spray on plugged equipments and use it only in well ventilated areas.
- Ask for MSDS.

#### PHYSICAL PROPERTIES

Binder	Polyurethane (PU) soluble in water
Color:	White
Dry to the touch (ASTM D-1640 ISO 1517):	30'
Completely dry(ASTM D-1640 ISO 1517 ):	24-48h'
Thickness of dry layer (ASTM D-823 ISO 2808 ):	20 μ/coat (2coats)
Adherence (ASTM D-3359 ISO 2409 ):	В
Theorical yield ( pintado en continuo ):	2,5 m <sup>2</sup>
Solvent:	Water / Alcohol
Product life:	(Well Stored) 5 years
Heat resistance of paint:	120°C
Condition for application:	Minimum Tº 8°C
	Surface T° 5-50°C
	Max. humidity 85% R.H.P

\*The adhesion tests have been done on steel plate.

#### CAUTION



APPEARANCE



#### LABEL



#### **CAP SISTEM**



Pocket Cap Medio - Medium

Gesso Primer

## PACKAGING

Nominal capacity 400 ml. Heat resistanve of packaging: <50°C Propellant: DME

Box (6 units) 205 X 140 X 200 mm.







Company certified according to quality standard ISO 9001:2000 ISO 14001:2004

Made in Europe.